AMERZINE®



DESCRIPTION

AMERZINE® corrosion inhibitor is an all-volatile, liquid, catalyzed oxygen scavenger for use in low-, medium- and high-pressure steam generating systems. AMERZINE® corrosion inhibitor controls ferrous and non-ferrous corrosion in feedwater, boilers, steam, and condensate lines with the use of hydrazine as the oxygen scavenger.

In addition to scavenging oxygen, AMERZINE® corrosion inhibitor passivates metal surfaces through the formation of protective oxide films thereby minimizing iron and copper deposits in the boiler.

AMERZINE® corrosion inhibitor may be used with DREWPLEX® AT boiler water treatment, standard treatment for low-pressure steam generating systems (0-32 bar), standard treatment for medium-pressure steam propulsion vessels (32-60 bar), and our ULTRAMARINE™ boiler water treatment program for high-pressure steam generating systems (60-84 bar).

APPLICATION & USE

Dosage, Testing, and Control

The continuous dosage of AMERZINE® corrosion inhibitor will depend upon the amount of dissolved oxygen in the feedwater. The colder the feedwater, the more dissolved oxygen there will be. Keep the feedwater temperature as close to 90°C, or higher, if possible. For starting up a new system, an estimated initial dosage of AMERZINE® corrosion inhibitor is 0.15 liters per ton of boiler water in the system. Daily testing of hydrazine in the boiler water using the AMERZINE® ampoule test kit determines the necessary dosage to maintain the concentration within the specified control range. If the system has been poorly passivated, the initial system "demand" for AMERZINE® corrosion inhibitor may require a higher dosage for the first few weeks until the system comes to stabilization.

Slug dosing and/or improper control of the hydrazine concentration will not provide adequate protection of the boiler system and may lead to accumulation of ammonia in the condensate with possible corrosion of copper alloy tubes.

Feed Points

For low-pressure steam generating systems, when there is feedwater recirculation, dose AMERZINE® corrosion inhibitor continuously after the feedwater recirculation offtake. Diluted AMERZINE® corrosion inhibitor may be fed with diluted DREWPLEX® AT boiler water treatment using

the DREW™ Beta Metering System. For low-pressure steam generating systems using AMERZINE® standard treatment, continuously dose diluted AMERZINE® corrosion inhibitor with diluted SLCC-A™ corrosion inhibitor using the DREW Beta Metering System to the feedwater line downstream of the feedwater recirculation offtake. If there is no feedwater recirculation, dose continuously to the feed pump suction.

If a gravity feed flowmeter arrangement is used, the dosage point should be to the feed or cascade tank. The chemical feed line should extend at least one (1) meter below the water surface to avoid volatilization of the product. For steam systems with deaerators, AMERZINE® corrosion inhibitor should be continuously dosed by pump to the storage section of the deaerator or to the feed pump suction.

Lay-up: AMERZINE® corrosion inhibitor can also provide protection for boilers during wet lay-up. For details, consult your Drew Marine representative.

TYPICAL PROPERTIES

Appearance: Clear, yellow liquid Odor: Mildly ammoniacal

pH: 11.0
Specific Gravity @ 25°C: 1.0
Boiling Point: 100°C
Flash Point (PMCC): None
Freeze Point: -13.8°C

NOTE: Always wear the appropriate personal protective equipment when using this product.

PACKAGING

AMERZINE® corrosion inhibitor is available in 25-liter containers (PCN 0005406).

IMPORTANT INFORMATION

Drew Marine maintains Safety Data Sheets on all of its products. Safety Data Sheets contain health and safety information for your development of appropriate product handling procedures to protect your employees.

Our Safety Data Sheets should be read and understood by all of your supervisory personnel and employees before using Drew Marine products.







400 Captain Neville Drive Waterbury, CT 06705 USA 1-973-526-5700 Drew-Marine.com

Copyright © Drew Marine. All Rights Reserved. All statements, information and data presented herein are believed to be accurate and reliable but are not to be taken as a guarantee, express warranty or implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which seller assumes legal responsibility, and they are offered solely for your consideration, investigation and verification. Statements or suggestions concerning possible use of this product are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe on any patent.